

DERWENT-ACC-NO: 1990-378693

DERWENT-WEEK: 199051

COPYRIGHT 1999 DERWENT INFORMATION LTD

TITLE: Cement compsn. with hardening
rapidity - contains terpeneol as hardening retardant,
organic poly:isocyanate, water hardening
cement, water and fillers

PATENT-ASSIGNEE: IMPERIAL CHEM IND PLC[ICIL]

PRIORITY-DATA: 1989GB-0028815 (December 21, 1989) ,
1989GB-0003326 (February
14, 1989) , 1989GB-0028815 (December 21, 1989)

PATENT-FAMILY:

PUB-NO	PAGES	PUB-DATE	MAIN-IPC
JP 02247217A		October 3, 1990	N/A
000	N/A		

APPLICATION-DATA:

PUB-NO	APPL-DATE	APPL-DESCRIPTOR	APPL-NO
JP 02247217A		N/A	
1990JP-0033609	February 14, 1990		

INT-CL (IPC): C08G018/30, C08L075/04 , C09D175/04

ABSTRACTED-PUB-NO: JP 02247217A

BASIC-ABSTRACT:

A hardening compsn contg (a) water-hardening cement, (b)
fillers, (c) organic
polyisocyanate, (d) terpeneol, and (e) water.

Pref the cement is portland cement; the fillers are sand,
clay (eg mica,
kaoline, or plastic chips of nylon polymer,

polyvinylchloride,
urea/formaldehyde polymer, acrylonitrile/butadiene/styrene
terpolymer, or
polystyrene; and the organic polyisocyanate is aliphatic
diisocyanate (eg
hexamethylene diisocyanate); aromatic diisocyanate (eg
tolylene-2,4-diisocyanate or m- or p-phenylene
diisocyanate) or alicyclic
diisocyanate (eg dicyclohexyl methane diisocyanate).

USE/ADVANTAGE - Hardening compsns useful for formation of
floor or wall.
(Provisional Basic previously advised in week 9046) @(10pp
dwg.No.0/0)

TITLE-TERMS: CEMENT COMPOSITION HARDEN RAPID CONTAIN
TERPINEOL HARDEN RETARD
ORGANIC POLY ISOCYANATE WATER HARDEN CEMENT
WATER FILL

DERWENT-CLASS: A93 L02

CPI-CODES: A12-R01A; L02-D07;

POLYMER-MULTIPUNCH-CODES-AND-KEY-SERIALS:

Key Serials: 0209 0231 0304 0307 3161 0377 0759 1096 1276
1283 1517 1731 2541
2694 2698 3275
Multipunch Codes: 014 034 04- 055 056 061 062 063 072 074
076 080 117 122 139
141 180 185 186 28& 393 58& 613 614 618 623 626 681 688

SECONDARY-ACC-NO:

CPI Secondary Accession Numbers: C1990-164886